



NORTHERN GEOTEXTILES, INC.

P.O Box 526 Fargo, ND 58107-0526

www.no-geo.com

Phone: 701-478-0460

Fax: 701-297-7648

Offices: Fargo

Northern Geotextiles, Inc. filter sock is made from Dupont SF Geotextiles and are nonwoven, spunbonded, continuous filament polypropylene that meet the following Minimum Average Roll Values (MARV)

Property	ASTM Test	Filter Sock SF32	Filter Sock SF40
		MARV	MARV
Grab Tensile (lbs)	D 4632	110	130
Elongation (%)	D 4632	>50	>50
Trapezoidal Tear (lbs)	D 4533	40	60
Puncture (lbs)	D 4833	30	41
Mullen Burst (psi)	D 3786	90	140
AOS (U.S. sieve no.)	D 4751	50	70
Permittivity (sec)	D 4491	1.3	0.8
Permeability (cm/sec)	D 4491	0.05	0.04
Water Flow (gal/min/sf)	D 4491	95	60
UV Stability (%)	D 4355	70	70
Roll Sizes			
4" Sock		250'	250'
6" Sock		100'	100'